


Technical Information






System Chrome silver







Paint system for rims with 35 Line





Properties: Paint system to have a chrome look effect on rims, product contains very fine aluminium parts.

Cleaning	70-10 Silicone Remover		1x		70-10 Silicone Remover		1x		Wipe dry
-----------------	-------------------------------	-----------------------------------------------------------------------------------	----	-----------------------------------------------------------------------------------	-------------------------------	------------------------------------------------------------------------------------	----	-------------------------------------------------------------------------------------	----------

30 Line Black Ground coat	30 Line Topcoat, direct gloss	50-15 50-20 50-30 Hardener	60-10 60-20 60-30 60-40 Reducer Universal		2:1+10%		1.3		2		30 min 60°C		P3000
----------------------------------	--------------------------------------	-----------------------------------	--------------------------------------------------	-----------------------------------------------------------------------------------	---------	------------------------------------------------------------------------------------	-----	-------------------------------------------------------------------------------------	---	-------------------------------------------------------------------------------------	-------------	-------------------------------------------------------------------------------------	-------

Alternative:

35 Line Black Underground Basecoat	35 Line Basecoat	60-20 Reducer Universal		2:1		1.3		2		approx. 10 min
-------------------------------------------	-------------------------	--------------------------------	------------------------------------------------------------------------------------	-----	------------------------------------------------------------------------------------	-----	-------------------------------------------------------------------------------------	---	--------------------------------------------------------------------------------------	----------------

35-M599 Basecoat	35-M599 Basecoat	50-15 Hardener		100:5		1.3		3-4 thin layers		approx. 10 min
-------------------------	-------------------------	-----------------------	-------------------------------------------------------------------------------------	-------	-------------------------------------------------------------------------------------	-----	--------------------------------------------------------------------------------------	-----------------	---------------------------------------------------------------------------------------	----------------

Clear coats	See TDS
--------------------	----------------

Safety instructions:

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH, Automotive Refinish Coatings Solutions, Europe, Glasuritstraße 1, 48165 Münster, Germany

04/2024